# REPORT DOCUMENTATION PAGE

Form Approved OMB NO. 0704-0188

Public Reporting burden for this collection of	information is estimated to average 1 hour per r	esponse, including the tim	me for reviewing instructions, searching existing data sources, gathering ng this burden estimates or any other aspect of this collection of		
and maintaining the data needed, and complet information, including suggestions for reducing	ing and reviewing the collection of information.  In this burden, to Washington Headquarters Services.	vices, Directorate for info	ormation Operations and Reports, 1215 Jefferson Davis Highway, Suite		
1204. Arlington. VA 22202-4302, and to the (	Office of Management and Budget, Paperwork R	Reduction Project (0704-0	0188,) Washington, DC 20503.		
1. AGENCY USE ONLY ( Leave Blank	2. REPORT DATE	15 October 2001	3. REPORT TYPE AND DATES COVERED		
			Final 4/20/00 - 4/19/01		
4 TITLE AND CLIDTIFF E			5. FUNDING NUMBERS		
ITTLE AND SUBTITLE     Hall & Seebeck Measurement System			DAAD 19-00-1-0149		
For Evaluation of Alloy Phase Stability Microstructure & Properties					
To Evaluation of Alloy Friase of	ability microstractare a repenies				
6. AUTHOR(S)			1		
David L. Olson					
Timothy R. Ohno					
7. PERFORMING ORGANIZATION	NAME(S) AND ADDRESS(ES)		8. PERFORMING ORGANIZATION		
Dept of Metallurgical and Materials Engineering			REPORT NUMBER MT-CWJCR-001-020		
Colorado School of Mines					
Golden CO 80401-1887					
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING / MONITORING		
			AGENCY REPORT NUMBER		
U. S. Army Research Office			P-40863-MS-RIP		
P.O. Box 12211			• l		
Research Triangle Park, NC 27709-2211					
Research Thangle Fark, INC 21109-2211					
11 CLIDDI EMENERADA NOTES					
11. SUPPLEMENTARY NOTES  The views arrivings and/or findings contained in this report are those of the author(s) and should not be construed as an official					
The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
Department of the Army position	n, policy or decision, unless so de	signated by other	посинснацон.		
12 - DICTRIDITION / AUAH ADU	TV STATEMENT	I	12 b. DISTRIBUTION CODE		
12 a. DISTRIBUTION / AVAILABILITY STATEMENT			120. DISTRIBUTION CODE		
Approved for public release;	distribution unlimited.				
reproved for paorie reseme,					
13. ABSTRACT (Maximum 200 words	)		<u> </u>		
Hall and Seebeck measur	ement systems have been si	pecified, purch	nased, facilitated and calibrated. These		
			proaches, based on electronic tools which		
systems are assisting in res	earch chorts to ucvetop new	anaryucar app	proactics, based on dictionic tools willen		
have served the electronic	industry well, to assess struc	tural materials	s used in defense assemblies and structures		
These electronic systems w	vill develop multiple measur	ements techniq	ques to assess alloy phase stability, aging,		
microstructure and properties. Seebeck coefficient measurements have already been correlated with the					
diffusible hydrogen content in alloy with high transition metal element contents. These results show promise for					
assessment of hydrogen effects in gun barrel steel, naval nickel aluminum bronze fasteners, and high strength					
steel welds. Hall and Seebeck measurements have been used to characterize the microstructure in alloy thin					
films. Research is in progress to develop electronic techniques to determine the susceptibility of sigma					
formation in superalloys.	These electronic techniques	will offer rapid	d non destructive microstructural		
assessment with quantitative	e data acquisition for easy l	ong term storas	ge of product quality assurance.		
1	•		- •		
	-#- *	医压压性过去			
14. SUBJECT TERMS		OCT 1 9 2001	15. NUMBER OF PAGES		
		, 10 to 1	5		
	e <del>en</del>	/N N/	IC PRIOR CORE		
		$\mathcal{H}_{I_{A}}$	16. PRICE CODE		
	المعاشين	1			
17. SECURITY CLASSIFICATION	18. SECURITY CLASSIFICATION	19. SECURITY C	CLASSIFICATION 20. LIMITATION OF ABSTRACT		
OR REPORT	ON THIS PAGE	OF ABSTRAC			
UNCLASSIFIED	UNCLASSIFIED	T .	ASSIFIED UL		
NSN 7540-01-280-5500			Standard Form 298 (Rev.2-89		

MASTER COPY: PLEASE KEEP THIS "MEMORANDUM OF TRANSMITTAL" BLANK FOR REPRODUCTION PURPOSES. WHEN REPORTS ARE GENERATED UNDER THE ARO SPONSORSHIP, FORWARD A COMPLETED COPY OF THIS FORM WITH EACH REPORT SHIPMENT TO THE ARO. THIS WILL ASSURE PROPER IDENTIFICATION. NOT TO BE USED FOR INTERIM PROGRESS REPORTS; SEE PAGE 2 FOR INTERIM PROGRESS REPORT INSTRUCTIONS.

### MEMORANDUM OF TRANSMITTAL

U.S. Army Research Office ATTN: AMSRL-RO-BI (TR) P.O. Box 12211 Research Triangle Park, NC 27709-2211

Reprint (Orig + 2 copies)	☐ Technical Report (Orig + 2 copies)			
Manuscript (1 copy)	☐ Final Progress Report (Orig + 2 copies)			
	Related Materials, Abstracts, Theses (1 copy)			
CONTRACT/GRANT NUMBER: DAAD 19-00-1-0149				
REPORT TITLE: Hall & Seebeck Measurement System For Evaluation of Alloy Phase Stability Microstructure & Properties				
is forwarded for your information.				
SUBMITTED FOR PUBLICATION TO (app	plicable only if report is manuscript):			

Sincerely,

Dant Ohm

34040MS David L. Olson Dept of Materials Science Colorado School of Mines Golden CO 80401-1890

Project Title: Hall and Seebeck Measurement System for the Evaluation of Alloy Phase Stability, Microstructure and Properties

Contract Number: DAAD 19-00-1-0149

#### **FINAL REPORT**

**Submitted to:** 

United States Army Research Office
Materials Science Division
% Dr. William M. Mullins
4300 South Miami Boulevard
P. O. Box 12211
Research Triangle Park, North Carolina 17709-2211

## Submitted by:

Dr. David L. Olson Principal Investigator J. H. Moore Dist. Professor Dept. of Met. and Mat. Eng. 303-273-3955 Dr. Timothy R. Ohno Co-Principal Investigator Associate Professor Dept. of Physics 303-273-3847

Colorado School of Mines Golden, Colorado 80401

#### Introduction

The use of electronic and magnetic analytical instrumentation to assess structure-property relationships as they relate to needs of the electronic industry has made it possible to produce high quality and reproducible devices. The ability to make property determination and quality control has made it possible. There have been significant advancements in these electronic and magnetic instrumentation as seen by their measurement sensitivity, reduction in instrument size, electronic controls and data acquisition and most important a sound fundamental understanding the correlation of the measurement with electronic and phase structure. Opportunities are now arising for the use of these established analytical instruments and techniques for phase and microstructure determination, phase stability and prediction of service life of structural materials, such as found in high performance engines, vehicles and weapon systems. The advent of non destructive evaluation of microstructure and properties is offering significant savings in both money and time in maintaining many defense systems.

The project was to purchase the electronic analytical systems for use as both for electronic property characterization and for the development of practices to assess microstructure, phase determination, phase stability and the prediction of remaining service life of structural component. The instruments purchased, which will be used with the existing comprehensive optical and electronic microscopy, x-ray diffraction and surface analytical systems at the Colorado School of Mines, are listed below:

## **DURIP Equipment Summary**

The equipment purchased is consistent with the proposed instruments described in the proposal.

## 1. Hall Measurement System

Manufacturer: Lake Shore Cryotronics, Inc., 64 E. Walnut St., Westerville, Ohio, 43081-2399; Fax: (614) 891-1392; Telephone: (614) 891-1392

1. 7507 Low Voltage Autoswitching, High Sensitivity Hall measurement system with sample holder and cards for samples from 1 ohm to 150 gigaohm and in a

temperature range from 77 K to 400 K. High output magnet power supply and Neslab CFT-300 recirculating chiller

2. 75014 Closed Cycle Refrigerator Sample Module with a compressor, rated for a temperature range between 15 K and 350K.

Total cost of system: \$179,953.

## 2. Seebeck Measurement System

Manufacturer: MMR Technologies, Inc. (1400 North Shoreline Boulevard, Suite A-5, Mountain View, CA 94043-1346; Fax: (650) 9629647; Telephone: (650) 962-9620

1. Seebeck Effect Measurement System, the model K20SB100-5R includes K-20 Programmable Temperature Controller with control software, two Extended Wide Temperature Range Thermal Stage Units, SB100 Seebeck Electronics and software (no computer)

2. Hardware for vacuum and pressure manifolds and control, computer interface (from assorted vendors), required for custom pumping arrangement.

Total cost of system: \$22,440

Both systems, which are permanently installed at CSM in Meyer Hall, have been tested, calibrated and are fully functional. The initial measurements on a wide variety of samples have shown promising results. For instance measurements on  $TiB_x$  - TiC and  $CrSi_x$  thin films show low Hall mobility but very high carrier concentration ( $\sim 10^{23}$  cm<sup>-3</sup>) for samples of low resistivity. In addition measurements on highly resistive, undoped CdTe and CdS thin films as well, have been made to demonstrate the full range of the system.

Our ability to measure conductive metal films with the Hall measurement system has also been performed and has demonstrated that it can produce high quality results that are very useful for our current and proposed studies in the development of advanced alloys based on electronic based alloy theories. The measurement of the hydrogen content in materials using the Seebeck measurement system is becoming an every day practice. Projects for which this equipment will be used are listed below. The project numbers indicate investigations that are currently funded by DoD.

## 1. PHACOMP Meter - Sigma Phase in Turbine Engines

New PHACOMP, the electron-based calculation technique, has been used to investigate nickel-based weldments. These calculations are important for predicting the tendency of austenitic alloys to precipitate topologically close-packed phases which adversely affect mechanical and corrosion properties. Since Phacomp and New Phacomp computations are based on the electronic filling of the d-band, Seebeck coefficient measurements should offer a direct measurement practice to determine the tendency of having a phase change in the these alloys. This new

electronic characterization capability allows for the development of direct nondestructive evaluation of the phase stability of parts in service, such as turbine blades. (ARO DAAD 19-01-1-0375)

## 2. Advanced Hydrogen Sensor for Materials

Both diffusible and trapped hydrogen contents are being measured in hydrogen storage materials and structural alloys. Seebeck measurements have been found to offer a rapid assessment of the hydrogen contents in alloys with substantial transition element contents. Techniques are been developed for steel weldments and gun barrel steel under ARO contract and an initial effort is under way to assess the hydrogen content in aluminum bronze fasteners, which were hydrogen charged by cathodic protection, for the U. S. Navy.

(Steel weldments; ARO DAAD 19-00-1-0149, barrel steel for Benet Arsenal, Marine fastners: U. S. NSWC).

## 3. Characterizing Thin Film Microstructure

The new equipment is being used to characterize thin film microstructure to develop predictive models for evolution of thin film microstructure and properties. These measurements will form an integral part of the graduate education for physics, metallurgy and materials science, as well as supporting research activities in the CSM Advanced Coating and Surface Engineering Laboratory.

### 4. Colloboration with Los Alamos National Laboratory

New NDE techniques for evaluating the metallurgical aging of plutonium alloys. The current project makes plutonium measurements at LANL, but surrogate materials have been measured with the Seebeck measurement system at CSM to assist in designing the LANL equipment..

5. Collaboration with U.S. Naval Surface Warfare Center NDE R and D Group
The equipment will be used in collaboration with Robert Denale (Head, Welding and
NDE R&D U.S. Naval Surface Warfare Center) to measure diffusible hydrogen
associated with welding of high strength steels. The high strength steel weld metal
program is being performed by other investigators under ONR Grant N00014-94-10694.

6. Collaboration with Army Laboratory

We have had discussions with U.S. Army Benet Laboratory in the use of advanced methods to measure hydrogen content in steels in gun barrels. Our new instrumentation will allow preliminary NDE studies with the guidance of Paul Cote (Benet Laboratory).

7. Measurement of properties of transparent conducting oxide coatings

Transparent conducting oxide coatings form an important part of display technologies, photovoltaics and window coatings. Rapid electrical characterization with Hall and Seebeck will be used to characterize and develop materials with superior properties.

8. Studies of semiconductor thin films for photovoltaic applications

The processing stages of photovoltaic modules have great impact on solar cell efficiency and stability. The cell properties will be correlated with measurements on both cells and sub-modules consisting of layers of the actual devices. This work is supported by DOE through its Thin Film Partnership.

## **ACKNOWLEDGEMENTS:**

The numerous investigators, who will be frequently using these instruments to further their work, will acknowledge the support of the DOD Equipment grant program.